

Application No. 10/522,093
Filed: January 21, 2005
TC Art Unit: 4172
Confirmation No.: 6846

AMENDMENTS TO THE CLAIMS

1. (ORIGINAL) A method of immobilizing a polymer hydrogel on the surface of a polymer substrate, whereby a composition containing at least one hydrogel-forming polymer and at least one non-toxic photoinitiator compound is applied to the surface of a polymer substrate to form a hydrogel layer at least in areas, and then the hydrogel layer is subjected to treatment with electromagnetic radiation, so that the hydrogel is immobilized on the surface of the polymer substrate, forming a hydrogel layer.
2. (CURRENTLY AMENDED) The method in Claim 1, whereby electromagnetic radiation in the ultraviolet to visible range of the spectrum, preferably in the range from 170 ~~m~~-nm to 600 nm, is used for immobilization.
3. (PREVIOUSLY PRESENTED) The method in Claim 1, whereby the hydrogel-forming polymer is polyvinylpyrrolidone-based, polyalkylene-glycol-based, polyvinyl-alcohol-based, polyethylene-imine-based or polyvinyl-amine-based.
4. (ORIGINAL) The method in Claim 3, whereby the polyvinylpyrrolidone-based polymer contains copolymers containing polyvinylpyrrolidone, derivatives of polyvinylpyrrolidone and their copolymers.
5. (PREVIOUSLY PRESENTED) The method in Claim 1, whereby the polymer substrate is made of a polymer material chosen from

Application No. 10/522,093

Filed: January 21, 2005

TC Art Unit: 4172

Confirmation No.: 6846

polyethylene, polypropylene, polyvinyl chloride, polycarbonate, SEBS or polyurethane or mixtures thereof.

6. (PREVIOUSLY PRESENTED) The method in Claim 1, whereby the polymer substrate is a dialyser, hose, catheter, stent or urinary catheter or at least part of one.

7. (PREVIOUSLY PRESENTED) The method in Claim 1, whereby the non-toxic photoinitiator compound is chosen from the group composed of flavins, flavones, flavonoids and their derivatives, as well as nicotinic acid amide and its derivatives and thioxanthone.

8. (ORIGINAL) The method in Claim 7, whereby the initiator compound is riboflavin, morin, rutin or a mixture thereof.

9. (ORIGINAL) The method in Claim 7, whereby the initiator compound is nicotinic acid amide.

10. (ORIGINAL) The method in Claim 7, whereby the initiator compound is thioxanthone.

11. (WITHDRAWN) A polymer substrate that has a polymer hydrogel layer immobilized, at least in areas on its surface, whereby the hydrogel layer also contains at least one non-toxic photoinitiator compound.

12. (WITHDRAWN) The polymer substrate in Claim 11, whereby the non-toxic photoinitiator compound is chosen from the group

Application No. 10/522,093

Filed: January 21, 2005

TC Art Unit: 4172

Confirmation No.: 6846

composed of flavins, flavones, flavonoids and their derivatives, as well as nicotinic acid and its derivatives and thioxanthone.

13. (WITHDRAWN) The polymer substrate in Claim 12, whereby the polymer substrate is made of a polymer material, chosen from polyethylene, polypropylene, polyvinyl chloride, polycarbonate, SEBS or polyurethane or mixtures thereof.

14. (WITHDRAWN) The polymer substrate in Claim 12, whereby the polymer substrate is a dialyser, hose, catheter, stent or urinary catheter or at least part of one.

15. (PREVIOUSLY PRESENTED) The method in Claim 2, whereby:
the hydrogel-forming polymer is polyvinylpyrrolidone-based, polyalkylene-glycol-based, polyvinyl-alcohol-based, polyethylene-imine-based or polyvinyl-amine-based;

the polyvinylpyrrolidone-based polymer contains copolymers containing polyvinylpyrrolidone, derivatives of polyvinylpyrrolidone and their copolymers;

the polymer substrate is made of a polymer material chosen from polyethylene, polypropylene, polyvinyl chloride, polycarbonate, SEBS or polyurethane or mixtures thereof;

the polymer substrate is a dialyser, hose, catheter, stent or urinary catheter or at least part of one;

the non-toxic photoinitiator compound is chosen from the group composed of flavins, flavones, flavonoids and their derivatives, as well as nicotinic acid amide and its derivatives and thioxanthone.

Application No. 10/522,093

Filed: January 21, 2005

TC Art Unit: 4172

Confirmation No.: 6846

16. (PREVIOUSLY PRESENTED) The method in Claim 15, whereby the initiator compound is riboflavin, morin, rutin or a mixture thereof.

17. (PREVIOUSLY PRESENTED) The method in Claim 15, whereby the initiator compound is nicotinic acid amide.

18. (PREVIOUSLY PRESENTED) The method in Claim 15, whereby the initiator compound is thioxanthone.

19. (WITHDRAWN) The polymer substrate in Claim 13, whereby the polymer substrate is a dialyser, hose, catheter, stent or urinary catheter or at least part of one.